

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-119537

(43)Date of publication of application : 25. 04. 2000

(51)Int. Cl. C08L101/00
C03C 27/12
C08L 21/00
C08L 23/00
C08L 31/04
C09K 3/10

(21)Application number : 10-298939 (71)Applicant : YOKOHAMA RUBBER CO LTD:THE
(22)Date of filing : 20. 10. 1998 (72)Inventor : KOIZUMI YUKIO
WATANABE JIRO
TAKEYAMA SHUICHI
YAMAUCHI SHIGERU
SERIZAWA TORU

(54) THERMOPLASTIC ELASTOMER COMPOSITION AND DOUBLE GLAZING USING THE SAME COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a thermoplastic elastomer composition excellent in water vapor transmission and heat distortion resistances and to provide a simply producible double glazing using the composition as a sealing material and a spacer and excellent in moisture permeation resistance without shifting the glass plates even at a high temperature.

SOLUTION: This thermoplastic elastomer composition is obtained by using a thermoplastic resin having ≤ 100 g/m².24 h water vapor transmission rate (30 μ m thickness) and a rubber providing ≤ 300 g/m².24 h water vapor transmission rate (30 μ m thickness) when crosslinked as raw materials and has a dispersed phase comprising an at least partially dynamically crosslinked rubber composition in a continuous phase of the thermoplastic resin.

LEGAL STATUS

[Date of request for examination] 01. 10. 2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

BEST AVAILABLE COPY

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998, 2003 Japan Patent Office

BEST AVAILABLE COPY